DONGGUAN COWINT NEW MATERIAL TECHNOLOGY CO.,LTD
No.2,West Industrial Road of Jiaoli,Zhongtang Town,Dongguan
Tel: +86-769-88882603 Web:www.cowint.com
E-mail: info@cowint.com

Technical data sheet

CTS-S613C Acrylic Polymer in Primary Forms

Dedicated to high-grade swimsuit cloth, nylon lycra and other functional fabric printing.

Characteristic : Excellent tensile strength and resilience, high fastness, no stick back, excellent manual manipulation, the vast number of dealers, material, printing plant validation is super swimsuit paste quality on the market.

The proportion:

Product	White or light color	Middle color	Deep color
CTS-S613W	80-100%	40-50%	0-20%
CTS-S613C	0-20%	50-60%	80-100%
CTA-F31	1-2%	1-2%	1-2%
Mesh No.	43-48T	43-48T	43-48T

The process：

Printing →Dry in natural→Finish

Curing Process:

Temperature:130℃ with 90s.

Advice：

1、Big goods must pass a small sample test before printing, the cloth of different treatment methods are different, some special waterproof material cannot reach washing water or sticky pull resistance, anti scratch for, suggested adding 5% CT30 additives, in order to improve the fastness;

2、The use of color should be in normal standard;

In verbal or written just the technical advice to show our Companies sincerity, but for our products ,the user companies still have your responsibility for test, to verify whether is suitable for the process and to use; Given the use of the products of our company process conditions are not my company control, and therefore should be fully responsible by the users themselves.